

PRODUCT:

D.E.P Sand


PLANT(S):

LINCOLN • SHREWSBURY

PARTICLE SIZE DISTRIBUTION

Sieve Size	Avg. % Passing	PA Spec
#200	3.7	0-10
#100	8	2-20
#50	17	7-40
#30	29	20-65
#16	49	40-80
#8	82	65-100
#4	98	80-100
3/8"	100	100

Note: This product meets PA 408 specification



We herewith certify that our material is crushed limestone, and is produced at our plant(s) specified above. Please be aware that results may vary, as they are dependent upon mineral deposit variations. Please call for updated test analysis.