

BRAND: EarthCEM™ Slag Cement
Grade: 120
Type: ASTM C989-18a
Report Date: August 2022

SOURCE LOCATION:
WALAN SCP, LLC
501 Christina Avenue
Wilmington, DE 19801
855.438.7524

CHEMICAL & PHYSICAL REQUIREMENTS	TEST RESULT	SPECIFICATION
Sulfur Trioxide (SO ₃), %	1.71	4.0 Max
Sulfur Sulfide (S), %	.72	2.5 Max
Blaine Surface Area, m ² /kg	623	—
Fineness Retained on 325 Mesh Sieve (45 micron), %	.2	20 Max
Air Content %	8.4	12 Max
Total Alkalies % (Na ₂ O + 0.658 K ₂ O)	.38	—
SLAG ACTIVITY INDEX		
7 Day: Individual, %	98	—
7 Day: Average of last 5, %	90	—
28 Day: Individual, %	135	110 Min
28 Day: Average of last 5, %	127.6	115 Min
COMPRESSIVE STRENGTH		
7 Day - Reference Cement, PSI	4732	—
28 Day - Reference Cement, PSI	5538	5000
7 Day - 50% Slag + 50% Reference Cement, PSI	4656	—
28 Day - 50% Slag + 50% Reference Cement, PSI	7352	—
TEST DATA ON REFERENCE CEMENT		
Total Alkalies % (Na ₂ O + 0.658 K ₂ O)	.79	0.60 - 0.90
C3S	52.8	—
C2S	21.6	—
C3A	4.82	—
C4AF	10.92	—
Blaine Surface Area, m ² /kg	370	260 Min

NOTE: Dashes in the specification column means "Not Applicable."



Certified by: *Jason Murtha*
Jason Murtha
WALAN SCP Operations Mgr.