

Gemcoat ZERO™

DESCRIPTION

Gemcoat ZERO™ is a solvent-based, water-resistant, Zero VOC sealer made from 100% acrylic polymer formulation that creates a full-gloss finish that protects and improves the appearance of architectural block.

PRODUCT HIGHLIGHTS

- Fast-drying: dry to the touch in 15 minutes
- Water-resistant yet vapor and air permeable
- Full-gloss finish
- Low film build application: 5 wet mils max
- Very durable
- Exceeds most state and federal VOC requirements
- Cleanable with commercially available surface cleaners

SURFACE PREPARATION

1. Stir product before applying.
2. Substrate should be dry and clean of any oil and dirt.

APPLICATIONS

Vertical or horizontal
Interior or exterior
Above grade

SUBSTRATES

Brick
Concrete
Pavers
Stucco
Masonry block

PACKAGING

5 gal (19 L) pail with EZ-pour spout lid

COLOR

Clear liquid

YIELD

- 423 sq ft/gal at 1.0 mil dry film thickness
- A test area is recommended to determine actual coverage rates.

STORAGE

- Store in clean, unopened containers in a dry area
- Flammable material
- Protect from ignition source

SHELF LIFE

12 months

VOC CONTENT

0.00 lbs/gal (359 g/L)

TECHNICAL DATA COMPOSITION

Gemcoat™ ZERO is a blend of resin and additives.

TYPICAL PROPERTIES

Property	Value
Solids and active ingredients, % by weight	27.16%
VOC content, lbs/gal (g/L)	0.00 lbs/gal
Specific gravity, kg/L	0.93819
Density, lbs/gal	7.83
Penetration, in (mm) average depth, depending upon substrate	N/A

*Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

TEST DATA

Property	Results	Test Method
Flash point, °F (°C)	0°F	ASTM D 3278
Performance Testing Of Gemcoat™ (Independent Lab Testing)		
Test/Agent	Duration	Test Result
Graffiti Clean	1 Hour	No effect
Formula 409	24 Hours	No effect
Hydrochloric Acid	3 Hours	No effect
Motor Oil	24 Hours	No effect
Magic Marker	4 Days	Formula 409
Carbon Paper	4 Days	removed mark.
#2 Pencil	4 Days	No damage

APPLICATION

1. Ensure area to be coated is dry and clean.
2. Gemcoat™ can be applied with air or airless spray, solvent-safe soft brush or solvent-safe 3/8" nap roller.
3. Product needs to dry 1 hour before re-coating.

DRYING

- Air dry 20 minutes at 77° F (22°C) with 65% relative humidity.

CLEAN UP

- Lacquer thinner.
- Acetone.

HEALTH | SAFETY | ENVIRONMENTAL

Flammable material.

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.yorkbuilding.com or by calling 800.673.2408.

For medical emergencies only, call Chem-tel 800.255.3924

FOR BEST PERFORMANCE

- Shake well before using.
- Protect any surface not intended to be touched by Gemcoat™ with a drop cloth to help with easy clean up.
- No dilution is needed.
- 4-6 mils wet film thickness is recommended.
- If spraying, use a .011 to .015 nozzle and adjust air pressure to achieve a smooth, continuous film.
- If rolling, use a solvent-safe 3/8" nap roller.
- If brushing, use a solvent-safe soft bristle brush.
- Proper application is the responsibility of the user.
- Make certain the most current versions of product data sheets and SDS are being used.

LIMITED WARRANTY NOTICE

York Building Products (YBP) warrants the surface coating (Gemcoat ZERO™) on sound, vertical ground face block on the project identified (in the warranty certificate) will not chip, crack, peel or yellow due to ultraviolet light for a period of seven (7) years from the date of substantial completion, provided:

- a.) Product was properly applied.
- b.) Surface has not been abused or abraded away.
- c.) Property owner gives written notice to YBP within thirty (30) days of discovery of the condition giving rise to the claim. This warranty is a limited warranty and only covers the product (Gemcoat ZERO™) needed to retreat areas as identified in the claim. It does not cover any other occurrence or condition, including for example failure of the coating due to:
 - Improper surface preparation or improper application or use of the product.
 - Structural movement or defects in the substrate.
 - Use of sub-standard building materials, faulty construction, poor workmanship, or inadequate building design.
 - Cracks or joint areas requiring caulking, sealants or re-pointing.
 - Abrasion or other damage to the surface to which product was applied.
 - Repair or subsequent work to the surface to which product was applied.
 - Deliberate act of negligence of persons or entities other than YBP.
 - Efflorescence or lime run.
 - Unusual natural occurrences or Acts of God such as wind storms, hail, tornadoes or hurricanes.

The owner's exclusive remedy against YBP shall be payment by YBP of the cost of replacement materials to re-treat specific areas that defective product has been applied, YBP shall have no liability for any labor costs, for any damage to the components of the building or any contents of the building, nor for consequential or incidental damages including but not limited to lost profits, sales, or revenues, loss of use of the building, costs of any substitute building, facilities, or services, or injury to person or other property. This limited warranty and the remedies provided in this limited warranty are exclusive and are given in lieu of any other warranty, express or implied warranty of merchantability or fitness for a particular purpose. There are no warranties that extend beyond the description in this limited warranty.